SURTEC®, Inc. *Surface Technology*

1880 N. MACARTHUR DR. TRACY, CA 95376 Telephone (209) 820-3700 Fax (209) 820-3793

"STATEMENT"

FP-500

REDUCED MAINTENANCE
ULTRA HIGH GLOSS FLOOR POLISH

DESCRIPTION:
"STATEMENT" by SURTEC utilizes a completely new polymer system to produce a floor polish with exceptional initial gloss, leveling, burnish response and durability. STATEMENT produces optimum results when maintained by periodic Ultra High Speed Buffing. Outstanding protection and appearance can be achieved with less time and effort than ever before, resulting in significant labor savings. STATEMENT is easy to apply and maintain, making it the product of choice where a floor finish must maintain excellent appearance with minimal maintenance.
STATEMENT exceeds the Coefficient of Friction safety standards of ASTM Designation D-2047.

APPLICATION - Use standard application procedures with a good quality rayon or synthetic blend string mop, or microfiber applicator, applying thin to medium coats of STATEMENT.

ROUTINE MAINTENANCE - Use SURTEC's LF-150 at 1 or 2 oz. per gallon of water for damp mopping or scrubbing prior to high-speed buffing. High speed buffing STATEMENT will prolong the life of the polish and increase safety and durability, as well as increase shine and appearance. A propane buffer equipped with THERMAL GLOSS pads will achieve optimum buffing results, but any good quality high speed (1000+ rpm) buffer will achieve excellent results.

RECOAT - Scrub the floor with a low speed buffer or automatic scrubber and blue or green (medium scrub) pads using SURTEC LF-150 at a dilution of 2 to 4 oz. per gallon of water to achieve a clean surface. Rinse the floor with clean water and let dry, then apply one or more coats of STATEMENT, allowing each coat to dry completely before applying the next coat. Upon drying, high speed buff the last coat applied for optimum results.

STRIPPING - If stripping is necessary, use SURTEC LOW ODOR STRIPPER according to label directions.

SPECIFICATIONS:

COLOR:	Milk white, stable emulsion, dries clear.
ODOR:	Sweet
pH:	8.5 ± 0.2
HMIS RATING	Health =1 Flammability = 0 Physical Hazard = 0
REFRACTOMETER SOLIDS:	28.0%
FLASH POINT:	None (C.O.C. Method)
VOC CONTENT	Less than 1% by weight
DRYING TIME:	30 minutes at 20°C. (68°F.), 50% relative humidity.
GLOSS:	96 (A.S.T.M. Test D-523, 60°)
SAFETY (slip resistance):	Exceeds requirements (A.S.T.M. Test D-2047)
SPECIFIC GRAVITY:	1.02
DENSITY:	8.5 pounds per gallon
LEVELING:	Excellent (A.S.T.M. Test D-2801)
POWDERING RESISTANCE:	Excellent (A.S.T.M. Test D-2048-82)
RECOATABILITY:	Excellent (A.S.T.M. Test D-3153-78)
PACKAGE SIZES:	4 x 1 gallon jugs 5 gallon Twin Pack (2 x 2.5 gal. bottles/box) 55 gallon drums

rev. 09/29/17

SURTEC warrants this product to be of consistent quality. SURTEC'S warranty is limited to the replacement of product proven defective. The user assumes all other risks and liabilities resulting from the use of this product. If you have any questions, please call SURTEC at (209) 820-3700.