SURTEC®, Inc. *Surface Technology*

1880 N. MACARTHUR DR. TRACY, CA 95376 Telephone (209) 820-3700 Fax (209) 820-3793

DURA GLOSS

FP-547

HIGH GLOSS FLOOR POLISH
ULTRA HIGH SPEED BUFFABLE

DESCRIPTION:
DURA GLOSS is a newly formulated floor finish combining SURTEC's time proven ULTRA technology with new state of the art polymer chemistry, designed to give superior gloss and durability at reduced costs. DURA GLOSS is best used under an Ultra High Speed Buffing program due to its excellent response to buffing. DURA GLOSS yields exceptional gloss, durability and leveling characteristics, maintaining its superior appearance while showing excellent resistance to scuffing and black marking. The superior durability of DURA GLOSS vastly extends the period between recoat cycles, providing additional savings in labor and materials. DURA GLOSS exceeds the coefficient of friction safety standards of ASTM Designation D-2047.

STRIPPING - If stripping is necessary, use SURTEC L.O.S, SUPER STRIP or THORO-STRIP according to label directions.

APPLICATION - Use standard application procedures with a good quality rayon or synthetic blend string mop, or microfiber applicator, applying thin to medium coats of DURA GLOSS.

ROUTINE MAINTENANCE - Use SURTEC's FLOOR SHINE High Speed Floor Maintainer at 1 or 2 oz. per gallon of water for damp mopping or scrubbing prior to high-speed buffing. Routine use of FLOOR SHINE with high speed buffing will increase the safety and durability of the floor polish, extending the time between recoats. High speed buffing DURA GLOSS will prolong the life of the polish and increase safety and durability, as well as increase shine and appearance. A propane buffer equipped with THERMAL GLOSS pads will achieve optimum buffing results, but any good quality high speed (1000+ rpm) buffer will achieve excellent results.

RESTORATION - Scrub the floor with a low speed buffer or automatic scrubber and red (light cleaning) pads using SURTEC LF-150 floor cleaner at a dilution of 1 to 2 oz. per gallon of water to achieve a clean surface. Let dry, then apply a solution 1 part FLOORSHINE diluted with 4 parts water in a manner similar to applying floor polish. Upon drying, high speed buff for optimum results.

RECOAT - Scrub the floor with a low speed buffer or automatic scrubber and blue or green (medium scrub) pads using LF-150 floor cleaner at a dilution of 2 to 4 oz. per gallon of water to achieve a clean surface. Rinse the floor with clean water and let dry, then apply one or more coats of DURA GLOSS, allowing each coat to dry before applying subsequent coats. Upon drying, high speed buff the last coat applied for optimum results.

SPECIFICATIONS:

COLOR:	Milk white, dries clear.
ODOR:	Sweet
pH:	8.6 ± 0.1
HMIS RATING	Health =1 Flammability = 0 Physical Hazard = 0
REFRACTOMETER SOLIDS:	24%
FLASH POINT:	None (C.O.C. Method)
GLOSS:	95 (A.S.T.M. Test D-523, 60°)
SPECIFIC GRAVITY:	1.07
DENSITY:	8.9 pounds per gallon
SAFETY (slip resistance):	Exceeds requirements (A.S.T.M. Test D-2047)
LEVELING:	Excellent (A.S.T.M. Test D-2801)
POWDERING RESISTANCE:	Excellent (A.S.T.M. Test D-2048-82)
RECOATABILITY:	Excellent (A.S.T.M. Test D-3153-78)
PACKAGE SIZES:	4 x 1 gallon jugs 5 gallon Twin Pack (2 x 2.5 gal. bottles/box) 55 gallon drums

rev. 09/13/18

SURTEC warrants this product to be of consistent quality. SURTEC'S warranty is limited to the replacement of product proven defective. The user assumes all other risks and liabilities resulting from the use of this product. If you have any questions, please call SURTEC at (209) 820-3700.