

SURTEC, Inc. *Surface Technology*

1880 N MACARTHUR DR. TRACY, CA 95376 Phone (209) 820-3700 Fax (209) 820-3793

SURTEC® *CERTIFIED GREEN* 955 ULTRA NZ FP-955 NON-ZINC HIGH GLOSS FLOOR POLISH EXCEPTIONAL DURABILITY/HIGH SPEED BUFFABLE

DESCRIPTION - 955 ULTRA NZ uses advanced acrylic polymer technology to deliver a superior quality floor polish that does not contain zinc, yet with the high gloss, durability, buffability, detergent resistance and ease of stripping of zinc metal interlock floor polishes. 955 ULTRA NZ was developed to respond exceptionally well when used in High Speed Maintenance Programs. 955 ULTRA NZ exceeds the coefficient of friction safety standards of ASTM Designation D-2047.

APPLICATION - Use standard application procedures with a good quality rayon or synthetic blend string mop, or microfiber applicator, applying thin to medium coats of 955 ULTRA NZ. Upon drying, high speed buff the last coat applied for optimum results. A propane buffer equipped with THERMAL GLOSS pads will achieve excellent buffing results, but any good quality high speed (1000+ rpm) buffer will achieve suitable results.

MAINTENANCE - The cleaner of choice for 955 ULTRA NZ prior to buffing is SURTEC 916 FLOOR SHINE NZ, diluted 1 to 2 ounces per gallon of water, applied with a mop, or scrubbed on with an automatic scrubber. Buff all areas with a high speed buffer. 916 FLOOR SHINE NZ cleans the floor AND increases the gloss and durability of the 955 ULTRA NZ when used in a high speed buffing maintenance program. If cleaning without buffing is desired, use SURTEC 912 NEUTRAL pH CLEANER, diluted 1 to 2 ounces per gallon of water, applied with a mop or scrubbed on with a floor buffer or automatic scrubber. 912 NEUTRAL pH CLEANER cleans thoroughly without dulling or leaving residue on the floor.

RECOAT - Scrub the floor with a low speed buffer or automatic scrubber and blue or green (medium scrub) pads using SURTEC 914 HEAVY DUTY CLEANER at a dilution of 2 to 4 ozs. per gallon of water to achieve a clean surface. Rinse the floor with clean water and let dry, then apply one or more coats of 955 ULTRA NZ. Upon drying, high speed buff the last coat applied for optimum results.

STRIPPING - If stripping is necessary, use SURTEC LOW ODOR STRIPPER according to label directions.

SPECIFICATIONS:

COLOR:	Milk white, stable emulsion, dries clear.
ODOR:	Mild, sweet
pH:	8.6 ± 0.1
HMIS RATING:	Health = 1 Flammability = 0 Physical Hazard = 0
REFRACTOMETER SOLIDS:	27%
VOC CONTENT:	Less than 1%
FLASH POINT:	None (C.O.C. Method)
DRYING TIME:	30 minutes at 20°C. (68°F.), 50% relative humidity.
COVERAGE:	2000 sq. ft. per gallon (average coverage on sealed floor)
GLOSS:	99 (A.S.T.M. Test D-523, 60°)
SPECIFIC GRAVITY / DENSITY:	1.03 / 8.6 pounds per gallon
ZINC OR HEAVY METAL CONTENT:	None
SAFETY (slip resistance):	Exceeds requirements (A.S.T.M. Test D-2047)
LEVELING:	Excellent (A.S.T.M. Test D-2801)
POWDERING RESISTANCE:	Excellent (A.S.T.M. Test D-2048-82)
RECOATABILITY:	Excellent (A.S.T.M. Test D-3153-78)
PACKAGE SIZES:	4 x 1 gallon jugs
.....	5 gallon Twin Pack (2 x 2.5 gal. bottles/case)

THE GREEN SYSTEM BY SURTEC®

Revised: 01/12/21

SURTEC warrants this product to be of consistent quality. SURTEC'S warranty is limited to the replacement of product proven defective. The user assumes all other risks and liabilities resulting from the use of this product. If you have any questions, please call SURTEC at (209) 820-3700.