

DURA GLOSS
FP-547
HIGH GLOSS FLOOR POLISH
ULTRA HIGH SPEED BUFFABLE

DESCRIPTION:

DURA GLOSS is formulated to offer exceptional gloss, excellent leveling and superb scuff and blackmark resistance at reduced costs. The superior durability of DURA GLOSS greatly extends the period between recoat cycles, providing additional savings in labor and materials. With its excellent burnish response, DURA GLOSS is best suited for use in high speed maintenance programs utilizing frequent burnishing to maintain a high level of appearance. DURA GLOSS exceeds the coefficient of friction safety standards of ASTM Designation D-2047.

DIRECTIONS:

APPLICATION - Use standard application procedures with a good quality rayon or synthetic blend string mop, or microfiber applicator, applying no more than three thin to medium coats of DURA GLOSS. Upon drying, high speed buff the last coat applied for optimum results. High speed buffing DURA GLOSS will prolong the life of the polish and increase safety and durability, as well as increase shine and appearance. A propane buffer equipped with THERMAL GLOSS pads will achieve excellent buffing results, but any good quality high speed (1000+ rpm) buffer will achieve suitable results.

ROUTINE MAINTENANCE - Use SURTEC's FLOOR SHINE High Speed Floor Maintainer at 1 or 2 ozs. per gallon of water for damp mopping or scrubbing prior to high-speed buffing. Routine use of FLOOR SHINE with high speed buffing will increase the safety and durability of the floor polish, extending the time between recoats.

RECOAT - Scrub the floor with a low speed buffer or automatic scrubber and blue or green (medium scrub) pads using LF-150 floor cleaner at a dilution of 2 to 4 ozs. per gallon of water to achieve a clean surface. Rinse the floor with clean water and let dry, then apply one or more coats of DURA GLOSS, allowing each coat to dry before applying subsequent coats. Upon drying, high speed buff the last coat applied for optimum results.

STRIPPING - If stripping is necessary, use SURTEC L.O.S, SUPER STRIP or THORO-STRIP according to label directions.

SPECIFICATIONS:

COLOR:	Milk white, stable emulsion, dries clear
ODOR:	Sweet
pH:	8.6 ± 0.2
SPECIFIC GRAVITY/DENSITY:	1.03 / 8.6 pounds per gallon
FLASH POINT:	None (C.O.C. Method)
VOC CONTENT:	Less than 1% by weight
HMIS RATING:	Health = 1 Flammability = 0 Physical Hazard = 0
REFRACTOMETER SOLIDS:	24%
GLOSS:	95 (A.S.T.M. Test D-523, 60°)
DRYING TIME:	30 minutes at 20°C. (68°F.), 50% relative humidity
COVERAGE:	2000 sq. ft. per gallon (average coverage on a sealed floor)
LEVELING:	Excellent (A.S.T.M. Test D-2801)
POWDERING RESISTANCE:	Excellent (A.S.T.M. Test D-2048-82)
RECOATABILITY:	Excellent (A.S.T.M. Test D-3153-78)
SAFETY (slip resistance):	Exceeds requirements (A.S.T.M. Test D-2047)
PACKAGE SIZES:	4 x 1 gallon jugs
.....	5 gallon Twin Pack (2 x 2.5 gal. bottles/box)
.....	55 gallon drums