



www.surtecsystem.com

**SURTEC Introduces...**

# **STATEMENT**

**THE LATEST TECHNOLOGY IN FLOOR FINISH**

**REDUCED MAINTENANCE · ULTRA HIGH GLOSS FLOOR POLISH**



**EXCEPTIONAL**

**GLOSS · LEVELING · BURNISH RESPONSE · DURABILITY**

The product of choice when ultra high gloss and minimal maintenance is required.

**Easy to apply. Easy to maintain.**

*Another 'Solution' from Surtec!*

**STATEMENT**  
 FP-500  
**ULTRA HIGH GLOSS**  
**LOW MAINTENANCE FLOOR POLISH**

**DESCRIPTION:**

STATEMENT utilizes a completely new polymer system to produce a floor polish with exceptional initial gloss, leveling, burnish response and durability. Outstanding protection and appearance can be achieved with less time and effort than ever before, resulting in significant labor savings. STATEMENT is easy to apply and maintain, making it the product of choice where a floor finish must maintain excellent appearance with minimal maintenance. Optimum results are achieved when maintained by periodic Ultra High Speed Buffing. STATEMENT is ideally suited for use in supermarkets and large retail stores, where a consistent, high level of gloss and appearance is required. STATEMENT exceeds the Coefficient of Friction safety standards of ASTM Designation D-2047.

**DIRECTIONS:**

**APPLICATION** - Use standard application procedures with a good quality rayon or synthetic blend string mop, or microfiber applicator, applying thin to medium coats of STATEMENT. Allow 30 minutes of dry time between coats or before opening to traffic. As many coats as needed may be applied without intercoat attack, provided each coat is allowed to dry completely. Note: On a bare, stripped floor, four or more coats may be required to achieve the highest level of gloss.

Although not necessary because of STATEMENT's high initial gloss, periodic high speed buffing of STATEMENT will increase shine and appearance, increase safety and durability and prolong the life of the polish. A propane buffer equipped with THERMAL GLOSS pads will achieve excellent buffing results, but any good quality high speed (1000+ rpm) buffer will achieve suitable results.

**ROUTINE MAINTENANCE** - Use SURTEC's LF-150 at 1 or 2 ozs. per gallon of water for damp mopping or scrubbing. Burnish as necessary for gloss recovery.

**RECOAT** - Scrub the floor with a low speed buffer or automatic scrubber and blue or green (medium scrub) pads using SURTEC LF-150 at a dilution of 2 to 4 ozs. per gallon of water to achieve a clean surface. Rinse the floor with clean water and let dry, then apply one or more coats of STATEMENT, allowing each coat to dry completely before applying the next coat. Upon drying, high speed buff the last coat applied for optimum results.

**STRIPPING** - If stripping is necessary, use SURTEC L.O.S., SUPER STRIP or ULTRA STRIP according to label directions.

**SPECIFICATIONS:**

COLOR: .....	Milk white, stable emulsion, dries clear
ODOR: .....	Sweet
pH: .....	8.5 ± 0.2
SPECIFIC GRAVITY/DENSITY: .....	1.02 / 8.5 pounds per gallon
FLASH POINT: .....	None (C.O.C. Method)
VOC CONTENT: .....	Less than 1% by weight
HMIS RATING: .....	Health = 1 Flammability = 0 Physical Hazard = 0
REFRACTOMETER SOLIDS: .....	28%
GLOSS: .....	96 (A.S.T.M. Test D-523, 60°)
DRYING TIME: .....	30 minutes at 20°C. (68°F.), 50% relative humidity
COVERAGE: .....	2000 sq. ft. per gallon (average coverage on a sealed floor)
LEVELING: .....	Excellent (A.S.T.M. Test D-2801)
POWDERING RESISTANCE: .....	Excellent (A.S.T.M. Test D-2048-82)
RECOATABILITY: .....	Excellent (A.S.T.M. Test D-3153-78)
SAFETY (slip resistance): .....	Exceeds requirements (A.S.T.M. Test D-2047)
PACKAGE SIZES: .....	4 x 1 gallon jugs
.....	5 gallon Twin Pack (2 x 2.5 gal. bottles/box)
.....	55 gallon drums